

BRP Manufacturing Company
637 North Jackson Street
Lima, Ohio 45802
Phone: 419-228-4441
Fax: 419-222-5010
Toll free: 800-858-0482



Specification Sheet

Material	Neoprene Rubber Sheet
BRP Style	CN70
Finish	Smooth (Fabric Finish is Available)
ASTM Callout	ASTM D2000 2BC710

Basic Requirements

Heat Aged, Test Method D 573, 70 h @ 100°C

Tensile Change	PSI	± 30% Max
Elongation Change	%	-50% Max
Hardness Change	Points	± 15

Oil immersion, Test Method D471, IRM 903 Oil, 70 h @ 100°C

Volume Change	% Max	+120
---------------	-------	------

Compression Set, Test Method ASTM D395 S, max, %22 h 22 hr @ 100C

Compression Set	%	80% Max
-----------------	---	---------

Operating Temperature Range -40 - 220° F